



Caratteristiche Victoria Conservation White Core

Carte delle superfici esterne

- Prodotte in pura cellulosa senza lignina
- Tamponata con carbonato di calcio (minimo 3% del peso)
- Gli estratti solubili in acqua sono minimi cioè inferiore allo 0,05% il cloruro e sotto lo 0,25% il solfato.

Anima centrale

- Alfa-cellulosa di alta qualità senza lignina e con buon punto di bianco
- Tamponata con carbonato di calcio (minimo 3%)
- Supera il Silver Tarnish Test e il Photographic Activity Test.

Adesivo

- Acquoso PVA con pH neutro
- Tamponata con carbonato di calcio (minimo 3%)
- Senza plasticizzanti

Test di invecchiamento accelerato :

TAPPI T.509 SU68

Valore del pH

alla produzione - pH8.9

dopo 100 anni -pH8.9

dopo 200 anni -pH8.9

dopo 300 anni -pH8.9

Sarcedo 18.05.2016

CANEVA RUGGERO

Via dei Molini 31H I - 36030 Sarcedo (VI) Italia ☎+39-0445.344.114 📠+39-0445.613.093
www.caneva.net e-mail: infocaneva@caneva.net P.I./VAT IT01718800244



Victoria Conservation White Core Specification

The surface and backing papers

- Made from chemically-treated pulp using pH sizing and lignin-free
- Blue wool scale (BWS) minimum rating 3+
- Buffered with calcium carbonate (> 3% by weight)
- The water-soluble extracts are minimal i.e. chloride below 0.05%, sulphate below 0.25%.
For extra defence it contains a buffer of calcium carbonate to guard against contamination by air-borne acid for the life of the board.

The Core

- High-quality alpha cellulose. Lignin-free and bright white throughout.
- Buffered with calcium carbonate (> 3% by weight)
- Passes the Silver Tarnish Test and Photographic Activity Test P.A.T.

The adhesive

- Aqueous PVA with neutral pH.
- Buffered with calcium carbonate (> 3% by weight)
- Is plasticiser-free.

Accelerated ageing test

TAPPI T.509 SU68

pH value

at production	-pH8.9
after 100 years	-pH8.9
after 200 years	-pH8.9
after 300 years	-pH8.9

Sarcedo 18.05.2016

CANEVA RUGGERO

Via dei Molini 31H I - 36030 Sarcedo (VI) Italia ☎+39-0445.344.114 📠+39-0445.613.093
www.caneva.net e-mail: infocaneva@caneva.net P.I./VAT IT01718800244